

# DuPont™ Krytox® XHT-NM and XHT-NMX

## Performance Lubricants

This grease is a special extreme high temperature grease with low oil evaporation and is thickened with a non-melting thickener to allow use at temperatures above the melting point of common greases. It has excellent lubrication over a broad temperature range. Krytox® XHT-NM series greases are nonflammable and chemically inert. Krytox® allows extended lubrication intervals and longer equipment life.

This grease is designed for use where the temperatures are in the 288°C (500°F) range and higher, where there is a danger of melting the standard

PTFE thickener. This grease uses a special non-melting high temperature thickener. The base oil is an extremely viscous oil that provides good viscosity and lower evaporation at high temperatures. The grease is for use in low speed bearings and will shear at high speeds, causing loss of oil. The oil in the grease can begin to slowly degrade at temperatures above 329°C (625°F) and this will occur at an increasing rate as temperatures increase. Relubrication could be required at these temperatures to achieve optimum life.

Typical uses include conveyor bearings.

	XHT-NM	XHT-NMX
NLGI Penetration Grade	2	2
Estimated Useful Temperature Range	-20/300°C (-4/572°F) with spikes to 330°C (626°F)	-15/350°C (5/662°F) with intermittent spikes to 400°C (752°F)
Pour Point	-25°C (-13°F)	-15°C (5°F)
Base Oil Viscosity, cSt		
20°C (68°F)	1,830	2,560
40°C (104°F)	500	738
100°C (212°F)	47	65
Oil Separation in 30 hr at 99°C (210°F), %	10	9
Oil Volatility in 22 hr at 260°C (500°F), % D972 modified	2.1	1.5
Appearance	White, creamy consistency	White, creamy consistency
Specific Gravity, 0°C (32°F)	1.99	1.99



*The miracles of science™*

## Compatibility with Metals

Due to their low surface tensions, Krytox® oils easily wet metallic surfaces and because of their inertness, Krytox® oils have little or no adverse effect on metals when the oil temperature is lower than 288°C (550°F). The behavior of Krytox® oils in the presence of many alloys has been studied using the Micro Oxidation-Corrosion Test developed by the Air Force Materials Laboratory.

In general, nickel and cobalt alloys are the most resistant to corrosion and are suitable for use with Krytox® up to 371°C (700°F). Carbon steel alloy suitability should be studied for uses above 288°C (550°F). Some types of stainless steel are

satisfactory at 316°C (600°F). A summary of metals compatible with Krytox® oils at various temperatures is given below.

Certain alloys have been found to cause catalytic depolymerization of Krytox® at high temperatures. At 316°C (600°F), for example, titanium alloys that contain aluminum function in this way. Aluminum alloy 2024 also catalytically depolymerizes Krytox® at 371°C (700°F). This depolymerization is considerably reduced in the absence of oxygen when an inert gas is substituted for the dry air flow. This suggests that the reactions involved are between the Krytox® and the oxide coating on the metal surface.

---

### Metals and Alloys Suitable for Use with Krytox® at Elevated Temperatures

---

Based on results of Micro Oxidation-Corrosion Tests, 72 hr at indicated temperature, 5 L dry air flow/hr, qualifying corrosion rate 0.4 mg/cm day

371°C (700°F)	Nickel alloys Cobalt alloys AMS 5547 steel
343°C (650°F)	AMS 5525 steel Titanium alloy Ti(6Al-6V-2Sn) Mg, Ag, Cr, V
316°C (600°F)	Types 301, 304, 316, 321, and 446 stainless steels N-155 Titanium alloy (13V-11Cr-3Al) Titanium alloy (6Al-4V) Aluminum alloy QQ-A-355 Bearing bronze
288°C (550°F)	Types 405, 410, and 440 stainless steels QQ-S-636, M-1, M-50, WB-49, and 52100 steels Titanium alloy Ti(8Mn) Copper

---

Below 288°C (550°F), most metal and alloys show little or no evidence of corrosion in the presence of Krytox®.

---

For more information or technical assistance, call:

(800) 424-7502

or visit us on the Web:

<http://www.krytox.com>

---

Or call the Krytox® hotline in the **United States** at (800) 424-7502, E-mail: [krytox@usa.dupont.com](mailto:krytox@usa.dupont.com)

**Canada** at 800-263-5924, E-mail: [products@can.dupont.com](mailto:products@can.dupont.com)

**Europe, Mideast, and Africa** at +32.3.543.1267, E-mail: [lubricants@lux.dupont.com](mailto:lubricants@lux.dupont.com)

**Asia/Pacific—Including India** at 886-2-2514-4434, E-mail: [krytox.lubricants@twm.dupont.com](mailto:krytox.lubricants@twm.dupont.com)

**Mexico and Central America** at +52-5-722-1150, [www.dupont.com.mx](http://www.dupont.com.mx)

**South America—All Countries** at 55-11-4166-8601, E-mail: [produtos.brasil@bra.dupont.com](mailto:produtos.brasil@bra.dupont.com)

---

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable. It is intended for use by persons having technical skill and at their own discretion and risk. Because conditions of use are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

Copyright © 2001 E.I. du Pont de Nemours and Company. All rights reserved.

