

DuPont™ Crastin® ST820 BK503

THERMOPLASTIC POLYESTER RESIN

Product Information

Common features of Crastin® thermoplastic polyester resin include mechanical and physical properties such as stiffness and toughness, heat resistance, friction and wear resistance, excellent surface finishes and good colourability. Crastin® thermoplastic polyester resin has excellent electrical insulation characteristics and high arc-resistant grades are available. Many flame retardant grades have UL recognition (class V-0). Crastin® thermoplastic polyester resin typically has high chemical and heat ageing resistance.

The good melt stability of Crastin® thermoplastic polyester resin normally enables the recycling of properly handled production waste. If recycling is not possible, DuPont recommends, as the preferred option, incineration with energy recovery (-24 kJ/g of base polymer) in appropriately equipped installations. For disposal, local regulations have to be observed.

Crastin® thermoplastic polyester resin typically is used in demanding applications in the electronics, electrical, automotive, mechanical engineering, chemical, domestic appliances and sporting goods industry.

Crastin® ST820 BK503 is an unreinforced, Super Tough polybutylene terephthalate resin for injection molding.

General information	Value	Unit	Test Standard
Resin Identification	PBT-HI	-	-
Part Marking Code	>PBT-HI<	-	ISO 11469
Rheological properties	Value	Unit	Test Standard
Moulding shrinkage, parallel	1.8	%	ISO 294-4, 2577
Moulding shrinkage, normal	1.7	%	ISO 294-4, 2577
Mechanical properties	Value	Unit	Test Standard
Tensile Modulus	1600	MPa	ISO 527-1/-2
Yield stress	36	MPa	ISO 527-1/-2
Yield strain	7	%	ISO 527-1/-2
Nominal strain at break	>50	%	ISO 527-1/-2
Strain at Break, 23°C, 50mm/min	130	%	ISO 527-1/-2
Flexural Modulus	1500	MPa	ISO 178
Flexural Strength	50	MPa	ISO 178
Charpy impact strength			ISO 179/1eU
23°C	N	kJ/m ²	
-30°C	N	kJ/m ²	
Charpy notched impact strength			ISO 179/1eA
23°C	85	kJ/m ²	
-30°C	10	kJ/m ²	
Izod notched impact strength			ISO 180/1A
23°C	60	kJ/m ²	
-40°C	10	kJ/m ²	
Izod impact strength			ISO 180/1U
23°C	N	kJ/m ²	
-30°C	N	kJ/m ²	
Thermal properties	Value	Unit	Test Standard
Melting temperature, 10°C/min	225	°C	ISO 11357-1/-3
Temp. of deflection under load			ISO 75-1/-2
1.8 MPa	50	°C	
0.45 MPa	100	°C	
0.45 MPa, annealed	145	°C	
Other properties	Value	Unit	Test Standard
Density	1220	kg/m ³	ISO 1183

Characteristics

- | | | | |
|------------|-----------------------------------------------------------------------------------------------------|------------------------------------------------------------------------------------------------|--------------------------------------------------------------|
| Processing | <ul style="list-style-type: none"> • Injection Moulding • Profile Extrusion | <ul style="list-style-type: none"> • Sheet Extrusion • Other Extrusion | <ul style="list-style-type: none"> • Coatable |
|------------|-----------------------------------------------------------------------------------------------------|------------------------------------------------------------------------------------------------|--------------------------------------------------------------|

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

Asia Pacific

Tel: +81 3 5521 8600

Europe/Middle East/Africa

Tel: +41 22 717 51 11



DuPont™ Crastin® ST820 BK503

THERMOPLASTIC POLYESTER RESIN

Regional Availability

- North America
- Europe

- Asia Pacific
- South and Central America

- Near East/Africa
- Global

Processing Texts

Injection molding

PREPROCESSING

Drying recommended = Yes

Drying temperature = 110-130 °C

Drying time, dehumidified dryer = 2-4 h

Processing moisture content = <0.04 %

PROCESSING

Melt temperature optimum = 250 °C

Melt temperature range = 240-260 °C

Mould temperature optimum = 80 °C

Mould temperature range = 30-130 °C

Chemical Media Resistance

Acids

- ✓ Acetic Acid (5% by mass) (23 °C)
- ✓ Citric Acid solution (10% by mass) (23 °C)
- ✓ Lactic Acid (10% by mass) (23 °C)
- ✗ Hydrochloric Acid (36% by mass) (23 °C)
- ✗ Nitric Acid (40% by mass) (23 °C)
- ✗ Sulfuric Acid (38% by mass) (23 °C)
- ✗ Sulfuric Acid (5% by mass) (23 °C)
- ✗ Chromic Acid solution (40% by mass) (23 °C)

Bases

- ✗ Sodium Hydroxide solution (35% by mass) (23 °C)
- ✓ Sodium Hydroxide solution (1% by mass) (23 °C)
- ✓ Ammonium Hydroxide solution (10% by mass) (23 °C)

Alcohols

- ✓ Isopropyl alcohol (23 °C)
- ✓ Methanol (23 °C)
- ✓ Ethanol (23 °C)

Hydrocarbons

- ✓ n-Hexane (23 °C)
- ✓ Toluene (23 °C)
- ✓ iso-Octane (23 °C)

Ketones

- ✓ Acetone (23 °C)

Ethers

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

Asia Pacific

Tel: +81 3 5521 8600

Europe/Middle East/Africa

Tel: +41 22 717 51 11



DuPont™ Crastin® ST820 BK503

THERMOPLASTIC POLYESTER RESIN

- ✓ Diethyl ether (23 °C)

Mineral oils

- ✓ SAE 10W40 multigrade motor oil (23 °C)
- ✗ SAE 10W40 multigrade motor oil (130 °C)
- ✗ SAE 80/90 hypoid-gear oil (130 °C)
- ✓ Insulating Oil (23 °C)

Standard Fuels

- ✗ ISO 1817 Liquid 1 (60 °C)
- ✗ ISO 1817 Liquid 2 (60 °C)
- ✗ ISO 1817 Liquid 3 (60 °C)
- ✗ ISO 1817 Liquid 4 (60 °C)
- ✓ Standard fuel without alcohol (pref. ISO 1817 Liquid C) (23 °C)
- ✓ Standard fuel with alcohol (pref. ISO 1817 Liquid 4) (23 °C)
- ✓ Diesel fuel (pref. ISO 1817 Liquid F) (23 °C)
- ✓ Diesel fuel (pref. ISO 1817 Liquid F) (90 °C)
- ✗ Diesel fuel (pref. ISO 1817 Liquid F) (>90 °C)

Salt solutions

- ✓ Sodium Chloride solution (10% by mass) (23 °C)
- ✓ Sodium Hypochlorite solution (10% by mass) (23 °C)
- ✓ Sodium Carbonate solution (20% by mass) (23 °C)
- ✓ Sodium Carbonate solution (2% by mass) (23 °C)
- ✓ Zinc Chloride solution (50% by mass) (23 °C)

Other

- ✓ Ethyl Acetate (23 °C)
- ✗ Hydrogen peroxide (23 °C)
- ✗ DOT No. 4 Brake fluid (130 °C)
- ✗ Ethylene Glycol (50% by mass) in water (108 °C)
- ✓ 1% nonylphenoxy-polyethyleneoxy ethanol in water (23 °C)
- ✓ 50% Oleic acid + 50% Olive Oil (23 °C)
- ✓ Water (23 °C)
- ✗ Water (90 °C)
- ✓ Phenol solution (5% by mass) (23 °C)

Symbols used:

- ✓ possibly resistant

Defined as: Supplier has sufficient indication that contact with chemical can be potentially accepted under the intended use conditions and expected service life. Criteria for assessment have to be indicated (e.g. surface aspect, volume change, property change).

- ✗ not recommended - see explanation

Defined as: Not recommended for general use. However, short-term exposure under certain restricted conditions could be acceptable (e.g. fast cleaning with thorough rinsing, spills, wiping, vapor exposure).

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

Asia Pacific

Tel: +81 3 5521 8600

Europe/Middle East/Africa

Tel: +41 22 717 51 11



DuPont™ Crastin® ST820 BK503

THERMOPLASTIC POLYESTER RESIN

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc. ISO Mechanical properties measured at 4.0mm (Hytrel® measured at 2 mm), IEC Electrical properties measured at 2.0mm, all ASTM properties measured at 3.2mm, and test temperatures are 23°C unless otherwise stated.

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents. Caution: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, discuss with your DuPont customer representative and read Medical Caution H-50103-4.

Copyright © 2014 DuPont or its affiliates. All Rights Reserved. The DuPont Oval Logo, DuPont™, The miracles of science™ and all products denoted with ® or ™ are registered trademarks or trademarks of E.I. du Pont de Nemours and Company or its affiliates.

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

Asia Pacific

Tel: +81 3 5521 8600

Europe/Middle East/Africa

Tel: +41 22 717 51 11

